
CONVEYOR AND PROCESS BELTS

TECHNICAL DATA SHEET

CODE NA-1094 **TYPE** **1M5 U2-U2 HP blue**

COMPOSITION

Conveying surface	Material	Polyurethane (TPU) - HP® system
	Thickness	0.20 mm *0.008 in.*
	Surface pattern	Smooth
	Colour	HP® blue
	Coefficient of friction	MF
Textile carcass	Material	Polyester (PET) - HP® system
	Plies no.	1
	Weft type	Rigid
Driving surface	Material	Polyurethane (TPU) - HP® system
	Thickness	0.20 mm *0.008 in.*
	Surface pattern	Smooth
	Colour	HP® blue



PRODUCT SYSTEM HP®

TECHNICAL SPECIFICATIONS

Total thickness	1.00 mm	*0.04*	*in.*
Weight	1.20 kg/m²	*0.24*	*lbs./sq.ft*
Elongation at 1%	5 N/mm	*29.0*	*lbs./in.*
Max. admissible pull	5 N/mm	*28.6*	*lbs./in.*
Temperature resistance (1) min.	-30 °C	*-22*	*°F*
Temperature resistance (1) max.	110 °C	*230*	*°F*

(1) Use of the belt with limit values may reduce its life.

Minimum radius / diameter (2)

■ Knife edge minimum radius	3 mm	*0,12*	*in.*
■ Bending roller min. diameter	6 mm	*0.24*	*in.*
■ Counter-bending roller min. diameter	30 mm	*1.18*	*in.*

(2) The above mentioned values depend on the type of CHIORINO joint recommende

Coefficient of friction on driving surface

■ Raw steel sheet	0.20 [-]
■ Laminated plastic/wood	0.25 [-]
■ Steel roller	0.20 [-]
■ Rubberized roller	0.30 [-]

Max. production width	2000 mm	*79*	*in.*

SUITABLE FOR

Food industry

FEATURES

Humidity influence	no
Suitable to metal detector	yes
Permanent antistatic dynamically (UNI EN ISO 21179)	yes
Static conductivity (UNI EN ISO 284)	no
Conveying on skid bed	yes
Conveying on rollers	yes
Conveying on skid bed on top and return	no
Troughed conveying	no
Swan neck conveying	no
Inclined conveying	no
Accumulators belts	no
Curved conveyor	no
Chemical resistances link	12

COMPLIANCES

REACH EC 1907/2006 Regulation and Amendments
EC 1935/2004 Regulation and Amendments
EC 2023/2006 Regulation and Amendments
EU 10/2011, 2017/752 Regulation and Amendments
HACCP (Hazard Analysis and Critical Control Points)
FDA (Food and Drug Administration)

NOTES

Issue: 07-07-2010 Last Update: 11-12-2018

DISCLAIMER
The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.


CHIORINO S.p.A. - VIA S. AGATA, 9 - 13900 BIELLA - ITALIA - P.O.B. 460 - TEL. +39-015-8489.1 - FAX +39-015.8496161
chiorino@chiorino.com - www.chiorino.com

CONVEYOR AND PROCESS BELTS

JOINING TECHNICAL DATA SHEET

CODE NA-1094 **TYPE** **1M5 U2-U2 HP blue**

Recommended joining procedure SINGLE Z



A = 80 mm
B = 10 mm

Other joining methods can be used:


Check our general catalogue to get further info on CHIORINO joining methods.

• Pressing

Heating press **P \ PL \ PLS**


Press settings	
Upper platen temperature	160 °C
Lower platen temperature	160 °C
Temperature gauge setting	160 °C
Curing time in press	3 min.
Pressure	3 bar
Film	TC-370 - PU HP blue film
Cement	---

1. Use the KM330 thermometer to check the effective temperature inside the belt. Place the thermometer gauge as shown by the drawing at side.



2. Allow the cooling cycle to be completed before removing the belt from the press.
3. A reliable strength of the joint is ensured, providing that temperatures reached by the press are those indicated in the table at side.
   A periodical inspection of the thermostats is recommended, to make sure they function correctly.

• Layout of components



Upper heated platen
Upper synthetic plate
Matt release paper (ML-2)
Film
Belt

Matt release paper (ML-2)
Lower synthetic plate
Lower heated platen

• Notes

Issued: 02-07-2010 Last Update: 30-01-2014

DISCLAIMER
The information contained in this document describes the features of the CHIORINO product as tested in a laboratory environment at a temperature of +23 degrees °C at 50% relative humidity. It does not necessarily reflect the conditions of industrial use and it does not guarantee the product to be suitable for certain applications. The client remains liable for the proper selection and correct use of the CHIORINO product. CHIORINO cannot be held responsible should damages arise from the use of its products. Necessary alterations to this data can be made without prior notice.

CHIORINO S.p.A. - VIA S. AGATA, 9 - 13900 BIELLA - ITALIA - P.O.B. 460 - TEL. +39-015-8489.1 - FAX +39-015.8496161
chiorino@chiorino.com - www.chiorino.com